

TECHNICAL DATASHEET

3460-2008 // BLACK BARRIER

| | |
|----------------|--------------------|
| MATERIAL | Chloroprene, black |
| COATING | - |
| SIZE(S) | 7-11 |
| PACKAGING UNIT | 144 pairs |
| CERTIFICATION | EN 388, EN ISO 374 |






DESCRIPTION

NITRAS BLACK BARRIER, chemical protective gloves, chloroprene, black, length 30 cm, flock lined, packed in pairs, for food contact

| | Material | Colour |
|------------------------|-------------|--------|
| Palm | Chloroprene | Black |
| Index finger and thumb | Chloroprene | Black |
| Back of the hand | Chloroprene | Black |
| Fingertips | Chloroprene | Black |
| Cuff / knitted wrist | Chloroprene | Black |

| Thickness (approx.) | mm |
|---------------------|-----|
| Finger | 0,6 |
| Palm | 0,6 |
| Cuff | 0,6 |

| EN 420:2003 + A1:2009 | | Test parameter | Performance level | Test result |
|---------------------------------------------------------------------------------------------------|-----------------------------------|----------------|-------------------|-------------|
| | | Dexterity | 1-5 | 5 |
| EN 388:2016 | | Test parameter | Performance level | Test result |
|  2111X | Abrasion resistance | | 1-4 | 2 |
| | Blade cut resistance (Coupe-Test) | | 1-5 | 1 |
| | Tear resistance | | 1-4 | 1 |
| | Puncture resistance | | 1-4 | 1 |
| | Blade cut resistance (TDM) | | A-F | X |
| ISO 374-1:2016/Typ B | | Test parameter | Class | Test result |
|  AKL | Methanol (A) | | 1-6 | 3 |
| | Sodium hydroxide 40 % (K) | | 1-6 | 6 |
| | Sulphuric acid 96 % (L) | | 1-6 | 2 |
| ISO 374-5:2016 | | Test parameter | Class | Test result |
|  | Penetration | | - | Passed |
| | Permeation | | - | Passed |